



TECHNICAL DATA/TESTING

Property	Test Method	Minimum Value
Tensile Strength	ASTM D412	62 lbs/in MD 47 lbs/in CD
Tensile Strength, UV Aging	ASTM D412	73 lbs/in MD 52 lbs/in CD
Tensile Strength, Weathered	ASTM D412	65 lbs/in MD 64 lbs/in CD
Pliability, 14 degrees F	ASTM D146	Pass
Water Vapor Transmission	ASTM E96	0.019 g/hr/sq.m (max)
Peel Adhesion	ASTM C794	19 lbs/in
Peel Adhesion, 7-day, Water	ASTM C794	13 lbs/in
Peel Adhesion, 210 Hrs, UV	ASTM C794	11 lbs/in
Cycle Over, 20 degrees F	ASTM C836	Pass